

ASTM F1292 Test Report

Date: August 28, 2007

There shall be one report for each play structure or functionally linked play structures and for each type of surface material. Each test shall comprise of a minimum of 3 impact locations per playspace or type of surfacing material with three drops from the same height to the same point. The report shall be descriptive enough to assist the user of the report in determining compliance with contracts and Standards. The CSA Z614-03 and the ASTM F1292 set minimum values as the Gmax shall not exceed 200 and the HIC shall not exceed 1000 from the drop height stipulated by the owner/operator prior to purchase.

Agency requesting the tests	Playground Site 2 Bay Swings	Manufacturer/Supplier/Installer of Surface
Name Calgary Board of Education	Name Hamptons	Name EVERPLAY Installation Inc.
Address Highfield Bldg, 3610 9 th St. S.E.	Address Hamptons Blvd.	Address 18 Automatic Rd., Unit 12
City Calgary State/Prov Alberta	City Calgary State/Prov Alberta	City Brampton State/Prov Ont
Zip/Postal T2G 3C5 Country	Zip/Postal Country	Zip/Postal L6S 5N5 Country
Contact name Raymond Hauck	Contact name	Contact name Henry Helps
Contact phone 403-777-7146	Contact phone	Contact phone 416-410-3113

Date of test:	August 28, 2007	Name of test apparatus:	Triax2000 current references
Description of surface(s):	Poured in place green surface		
Type:	Unitary	Product name:	EVERPLAY
Date installed:	August 2007	Critical height:	>10'
Thickness of surface material:	100mm	maximum:	110mm
		Minimum:	90mm
		average:	100mm
Evenness (comment on wear patterns and disruption):			
Seams: location:	None	gaps and condition:	None
		level across seams:	Na
Fasteners:	None	type:	
		condition:	
Weather condition of test:	Sunny with some cloud	frozen:	No
		dry:	Yes
		wet:	No
Surface condition;	New and in good condition		
Temperature: ambient air:	22.6C	surface temperature taken 6" depth for loose fill or 1/2" depth for unitary:	28.4C
Other conditions or observations:			
Mats, walkways or ramps;		number:	
		condition:	
		requires impact test:	yes/no
Pictures (file names); general playground		test locations:	

The drop height each test location shall be the greater of the critical height for the surface material, the fall height for the play structure as stated in the relevant playground Standard or the height specified by the owner/operator prior to purchase. The drop height is physically measured. The drops are performed from the same drop height to the same point on the surface.

Drop #	Drop height	Drop location in relation to structure	Picture	Velocity cm/sec	Gmax	HIC
1	3.05m	Top of swing support southwest swing bay	DSC8272	767	92	507
2				767	98	547
3				767	97	519
Av. 2&3					98	533
Drop #	Drop height	Drop location in relation to structure	Picture	Velocity	Gmax	HIC
1	3.05	Top of swing support southeast swing bay	DSC8273	770	112	704
2				770	115	712
3				770	115	713
Av. 2&3					115	713
Drop #	Drop height	Drop location in relation to structure	Picture	Velocity	Gmax	HIC
1	3.05	Top of swing support north east swing bay	DSC8274	767	108	645
2				767	110	668
3				767	114	692
Av. 2&3					112	680

The results herein reflect the performance of the tested playground surface at the time of testing and at the temperature(s) and ambient conditions reported. Performance will vary with temperature, moisture content and other factors.

Test performed by:	Rolf Huber	Authorized signature:	
--------------------	------------	-----------------------	--