

ASTM F1292 Test Report

Date: June 10, 2008

There shall be one report for each play structure or functionally linked play structures and for each type of surface material. Each test shall comprise of a minimum of 3 impact locations per playspace or type of surfacing material with three drops from the same height to the same point. The report shall be descriptive enough to assist the user of the report in determining compliance with contracts and Standards. The CSA Z614-03 and the ASTM F1292 set minimum values as the Gmax shall not exceed 200 and the HIC shall not exceed 1000 from the drop height stipulated by the owner/operator prior to purchase.

Agency requesting the tests	Playground Site	Manufacturer/Supplier/Installer of Surface
Name Town of Amhurstburg	Name Toddy Jones, Net Climber	Name Everplay Installation
Address 512 Sandwich St.	Address	Address 18 Automatic Rd, Unit 12
City Amhurstburg State/Prov ON	City Amherstburg State/Prov ON	City Brampton State/Prov ON
Zip/Postal Country CAN	Zip/Postal	Zip/Postal L6S 5N5
Contact name Lou Zarlenga	Contact name	Contact name Henry Helps
Contact phone (519) 736-3664	Contact phone	Contact phone 416 410-3056

Date of test:	June 10, 2008	Name of test apparatus:	Triax 2000
Description of surface(s):	Poured Rubber		
Type:	Synthetic	Product name:	Everplay
Date installed:	N/A	Critical height:	> 2.3 m
Thickness of surface material:	N/A	maximum:	11.3 cm
		minimum:	10.5 cm
		average:	10.8 cm
Evenness (comment on wear patterns and disruption):			
Seams: location:	None	gaps and condition:	
level across seams:			
Fasteners:	N/A	type:	
condition:			
Weather condition of test:	Sunny, warm	frozen:	
dry:		wet:	Yes
Surface condition:			
Temperature: ambient air:	20.7 C	surface temperature taken 6" depth for loose fill or 1/2" depth for unitary:	23.1 C
Other conditions or observations:			
Mats, walkways or ramps;	N/A	number:	
condition:		requires impact test:	no
Pictures (file names); general playground	See below	test locations:	See below

The drop height each test location shall be the greater of the critical height for the surface material, the fall height for the play structure as stated in the relevant playground Standard or the height specified by the owner/operator prior to purchase. The drop height is physically measured. The drops are performed from the same drop height to the same point on the surface.

Drop #	Drop height	Drop location in relation to structure	Picture	Velocity cm/sec	Gmax	HIC
1	2.3 m	South end	DSC_0328	668	71	325
2				668	72	319
3				668	73	323
Av. 2&3					72	321
Drop #	Drop height	Drop location in relation to structure	Picture	Velocity	Gmax	HIC
1	2.3 m	Inside middle	DSC_0329	668	70	307
2				668	69	306
3				668	69	308
Av. 2&3					69	307
Drop #	Drop height	Drop location in relation to structure	Picture	Velocity	Gmax	HIC
1	2.3 m	North end	DSC_0330	668	74	309
2				668	73	297
3				668	75	316
Av. 2&3					74	307

The results herein reflect the performance of the tested playground surface at the time of testing and at the temperature(s) and ambient conditions reported. Performance will vary with temperature, moisture content and other factors.

Test performed by:	Jonathan Huber	Authorized signature:
--------------------	----------------	-----------------------