

ASTM F1292 Test Report

Date: August 29, 2006

There shall be one report for each play structure or functionally linked play structures and for each type of surface material. Each test shall comprise of a minimum of 3 impact locations per playspace or type of surfacing material with three drops from the same height to the same point. The report shall be descriptive enough to assist the user of the report in determining compliance with contracts and Standards. The CSA Z614-03 and the ASTM F1292 set minimum values as the Gmax shall not exceed 200 and the HIC shall not exceed 1000 from the drop height stipulated by the owner/operator prior to purchase.

Agency requesting the tests	Playground Site Infinity Climber	Manufacturer/Supplier/Installer of Surface
Name Windsor, Parks & Recreation,	Name Boundless Playground	Name EVERPLAY Installation Inc.
Address. 2450 McDougall St	Address Riverside Dr.	Address 18 Automatic Rd., Unit 12
City Windsor State/Prov ON	City Windsor State/Prov ON	City Brampton State/Prov ON
Zip/Postal N8X 3N6 Country	Zip/Postal Country	Zip/Postal L6S 5N5 Country
Contact name Heidi Baillergeon	Contact name	Contact name Henry Helps
Contact phone 519-253-2300	Contact phone	Contact phone 416-410-3056

Date of test:	August 25, 2006	Name of test apparatus:	Triax2000 current references
Description of surface(s):	Poured in place with green EPDM topping		
Type:	Unitary	Product name:	EVERPLAY
Date installed:	August 2006	Critical height:	>3m
Thickness of surface material:	90mm	maximum:	100mm
Minimum:	50mm	average:	80mm
Evenness (comment on wear patterns and disruption):	Even across the surface		
Seams: location:	Na	gaps and condition:	level across seams:
Fasteners:	Na	type:	condition:
Weather condition of test:	Warm and sunny	frozen:	dry: Yes wet:
Surface condition;	New		
Temperature: ambient air:	27.5C	surface temperature taken 6" depth for loose fill or 1/2" depth for unitary:	35.8C
Other conditions or observations:			
Mats, walkways or ramps;	number:	condition:	requires impact test: yes/no
Pictures (file names); general playground	See each drop	test locations:	As directed by client

The drop height each test location shall be the greater of the critical height for the surface material, the fall height for the play structure as stated in the relevant playground Standard or the height specified by the owner/operator prior to purchase. The drop height is physically measured. The drops are performed from the same drop height to the same point on the surface.

Drop #	Drop height	Drop location in relation to structure	Picture	Velocity cm/sec	Gmax	HIC
1	2.4m	Top of infinity climber at north end	DSC5724	683	97	494
2				683	102	550
3				683	101	516
Av. 2&3					102	533
Drop #	Drop height	Drop location in relation to structure	Picture	Velocity	Gmax	HIC
1	2.4m	Top of infinity hand over hand climber	DSC5725	683	87	392
2				686	92	447
3				686	93	445
Av. 2&3					93	446
Drop #	Drop height	Drop location in relation to structure	Picture	Velocity	Gmax	HIC
1	2.4m	Top of infinity climber south side	DSC5726	683	86	398
2				683	83	360
3				683	89	414
Av. 2&3					86	387

The results herein reflect the performance of the tested playground surface at the time of testing and at the temperature(s) and ambient conditions reported. Performance will vary with temperature, moisture content and other factors.

Test performed by:	Rolf Huber	Authorized signature:	
--------------------	------------	-----------------------	--